



**GABION WALLS
AUSTRALIA**

SPECIFICATION

5mm Galvanised 50x50

Manufacture

Produced from hard drawn steel wire electrically welded at each intersection.

Mesh Aperture

The mesh openings shall be square and of a nominal dimension of 50mm centre to centre, resulting in a 441 individual welds per 1 sqm.

Mesh Wire

The nominal wire diameter shall be 5mm.

Coating

Wire shall be manufactured from zinc-coated steel wire.

Tensile Strength

The tensile strength shall be in the range of 415-585 MPa as per ASTM A974-97

Spiral Binders

Spiral binders shall be the preferred method of panel connectivity. Each spiral binder shall pass through the aperture of the mesh twice per opening ensuring a connection at every 25mm interval.

1800 87 00 47

www.gabionwalls.com.au